

# PAROC Hvac Lamella Mat AluCoat Fix

PAROC Hvac Lamella Mat AluCoat Fix is a self-adhesive ventilation and air conditioning duct insulation mat made of non-combustible PAROC® stone wool. The product is designed for thermal and condensation insulation of circular and rectangular ductwork in HVAC systems. It is suitable for indoor and outdoor pipes and HVAC equipment and can withstand medium temperatures of up to 50 °C. For outdoor installations, to maintain the integrity of the AluCoat-facing, the product must be protected from weather conditions with an additional covering. With Fix adhesion layer PAROC Hvac Lamella Mat AluCoat Fix makes installation quick and easy.

Its perpendicular fiber orientation maintains stiffness to preserve its designed thickness on all edges, guaranteeing consistent insulation performance and enhancing the overall efficiency of the HVAC system.

It is reinforced with an AluCoat facing, a water vapour-resistant barrier which together with taped joints reduces condensation risk and vapour permeability. The adhesive layer is protected by peel-off foil which ensures the durability of the connection and does not lose its properties over time. PAROC provides the necessary accessories for safe and complete installation, including: PAROC Hvac AluCoat Tape and PAROC Hvac Alu Tape.



## Product Data Sheet

2026-03-24

Dimensions (mm)	Width x Length	Thickness
	1000 x 2500	100
	1000 x 3000	80
	1000 x 4000	60
	1000 x 5000	50
	1000 x 6000	40
	1000 x 8000	30
	1000 x 9000	25
	1000 x 10000	20

<b>Nominal Density</b>	35 kg/m <sup>3</sup>
<b>Package Type</b>	Plastic packs on pallet
	Other dimensions are available on request.

<b>Product characteristics according to EN 14303</b>	Designation Code	MW-EN 14303-T4-ST(+)-50-WS1-MV2-CL10
	DoP Number	40236
	Thickness Tolerance, T	T4
	Reaction to Fire, Euroclass	B-s1,d0: 20 - 40 mm A2-s1,d0: 50 - 100 mm
	Maximum Service Temperature - Dimensional Stability	50 °C
	Water Absorption, Short Term, W <sub>p</sub>	≤ 1 kg/m <sup>2</sup>
	Water Vapour Diffusion Resistance	MV2

Trace Quantity of Water-soluble Chloride Ions	≤ 10 ppm
Thermal Conductivity, $\lambda_D$	See table below

°C	10	40	50
$\lambda_D$ W/(m*K)	0.038	0.043	0.047

## Fire Properties

The manufacturer recommends use of the product when the temperature of the isolated medium will not exceed +50 °C due to the adhesive layer. Surface temperature of the facing must not exceed +80°C (temperature restriction determined in accordance with heat resistance adhesive).

PAROC Stonewool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C while the fire protecting properties remain unchanged. Stone wool has a high melting point of over 1000°C (internal test method).

## Environmental Properties

The European Certification Board for Mineral Wool products (EUCEB) trademark on our products confirms that PAROC Stonewool fibre fulfils the bio solubility requirements of EU directive No. 1272/2008. The German RAL quality mark confirms that the bio solubility and safety requirements are met according to the German technical regulation TRGS905.

PAROC Stonewool is made of stone. The volume of the product is ~98% air and only ~2% fiberized stone. The excellent properties of the product are based on the properties of the raw materials. PAROC Stonewool maintains its insulating ability and dimensions throughout the reference service life of the the building, which is considered to be minimum 50 years.

PAROC Stonewool is reusable and can be recycled into new stone wool products.

## Certificates and Approvals

EC Certificate of Conformity	0809-CPR-1016
------------------------------	---------------

## Storage and Installation

PAROC products should be stored indoors, in a dry location, away from heat sources.

Installation in accordance with the manufacturer's instructions.

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Paroc makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. Paroc reserves the right to modify this document without prior notice. PAROC is a registered trademark of Paroc Group Oy. This data sheet is valid in following countries: international use (general information).