

PAROC Pro Segment WR 140

PAROC Pro Segment WR 140 is a ready cut segment made of non-combustible stone wool pipe section with outstanding water repellency, designed for thermal insulation of medium and large-size pipe elbows in industrial process pipework. These prefabricated insulation parts provide the best insulation solution for large pipe elbows without thermal bridges.

PAROC WR products are an excellent tool for minimizing the risk of CUI (corrosion under insulation), keeping the outstanding water repellent properties at elevated temperatures. PAROC WR products are safe to use in combination with painting operations.

PAROC Pro Segments are also available with AluCoat facing and/or as double layer solutions.



Product Data Sheet 4.2.2026

Dimensions (mm)	Inner Diameter	Thickness
	114 - 914	30 - 160

Nominal Density	140 kg/m ³
	Other dimensions are available on request.

Product characteristics according to EN 14303	Designation Code	MW-EN 14303-T8/T9-ST(+)-680-WS1-CL10
	DoP Number	40199
	Thickness Tolerances, T	T8/T9
	Reaction to Fire, Euroclass	A1 _l
	Maximum Service Temperature - Dimensional Stability	680 °C
	Water Absorption, Short Term WS, Wp	≤ 1 kg/m ²
	Trace Quantity of Water-soluble Chloride Ions	≤ 10 ppm
	Thermal Conductivity, λ _D	See table below

°C	10	50	100	150	200	300	400
λ _D W/(m*K)	0.038	0.041	0.047	0.054	0.063	0.085	0.110

Fire Properties	PAROC Stonewool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C while the fire protecting properties remain unchanged. Stone wool has a high melting point of over 1000°C (internal test method).
------------------------	---

Moisture Properties	PAROC WR Pipe Sections are providing a very low water absorption (average water absorption level <0,1 kg/m ² after 300°C/24h prebake) according to EN 13472, based on 3rd-party testing in 2019 and internal testing in 2023-2024.
----------------------------	---

Environmental Properties

The European Certification Board for Mineral Wool products (EUCEB) trademark on our products confirms that PAROC Stonewool fibre fulfils the bio solubility requirements of EU directive No. 1272/2008. The German RAL quality mark confirms that the bio solubility and safety requirements are met according to the German technical regulation TRGS905.

PAROC Stonewool is made of stone. The volume of the product is ~98% air and only ~2% fiberized stone. The excellent properties of the product are based on the properties of the raw materials. PAROC Stonewool maintains its insulating ability and dimensions throughout the reference service life of the the building, which is considered to be minimum 50 years.

PAROC Stonewool is reusable and can be recycled into new stone wool products.

Certificates and Approvals

EC Certificate of Conformity 0809-CPR-1016

PAROC WR products are safe to use in combination with painting operations: PAROC WR products are 3rd party tested, passing the requirements of the most stringent class of the LABS conformity (paint wetting impairment) standard, VDMA 24364.

MED Module B No. 74480/A2

UK Module B No. 74465/A2

Storage and Installation

PAROC products should be stored in packaging protected against external weather conditions.

Installation in accordance with the design assumptions or based on the manufacturer's instructions.

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Paroc makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. Paroc reserves the right to modify this document without prior notice. PAROC is a registered trademark of Paroc Group Oy. This data sheet is valid in following countries: international use (general information).